



Enriching lives through innovation

Adhesive Technical Support Europe

Comparison of Araldite[®] 2015
(Araldite[®] AV 5308 / Hardener HV 5309-1)

& Araldite[®] 2015-1
(Araldite[®] AV 5308 / Hardener HV 5309-2)

NEW PRODUCT DEVELOPMENT REPORT

PREPARED BY

Laurent CHOUVET
HUNTSMAN ADVANCED MATERIALS
Klybeckstrasse 200
4057 BASEL
Switzerland

Email: laurent_chouvet@huntsman.com

INTRODUCTION

In order to provide more user friendly and sustainable products to our customers, we have developed a new system called Araldite[®] 2015-1, which is equivalent in performance to the Araldite[®] 2015.

The following side by side report was issued to compare directly performances of the standard Araldite[®] 2015 with the new system Araldite[®] 2015-1. Processing parameters like density, mix ratios in weight & volume are the same with exception of slightly reduced pot-life and higher thixotropy.

RESULTS & DISCUSSION

Unless otherwise stated, the figures given below were all determined by testing standard specimens made by lap-jointing 114 x 25 x 1.6 mm strips of aluminium alloy. The joint area was 12.5 x 25 mm in each case. Cure conditions : 16h/40 °C

Functional properties

	Hardener HV 5309-1 (Araldite 2015)	Hardener HV 5309-2 (Araldite [®] 2015-1)
Aspect	Beige soft paste	Beige soft paste
Viscosity	Thixotropic	Highly thixotropic
Mix Ratio	100:100 (wt and vol)	100:100 (wt and vol)


Reactivity

	Araldite [®] 2015	Araldite [®] 2015-1
Pot life (100 g)	80 - 90 min.	45 - 55 min.


Time to reach a specific lap shear strength on sandblasted aluminium at different temperatures.

Time to reach Lap Shear Strength	Araldite [®] 2015	Araldite [®] 2015-1
1 MPa @ 15 °C	6 hours	6 hours
10 MPa @ 15 °C	16 hours	15 hours
1 MPa @ 23 °C	4 hours	4 hours
10 MPa @ 23 °C	8 hours	8 hours
1 MPa @ 40 °C	1 hour	1 hour
10 MPa @ 40 °C	2 hours	3 hours

Lap Shear Strength (LSS) on different substrates (ISO 4587)




Metal substrates : sandblasted & degreased with acetone




Plastic substrates : abraded & degreased with isopropanol

Lap Shear Strength vs temperature (ISO 4587)

Cure 7 days at RT



Cure 24 hours at 23°C + 30 minutes at 80°C



Tensile properties (ISO 527)

Cure 16 hours at 40°C

	Tensile modulus (MPa)	Tensile strength (MPa)	Elongation at break (%)
Araldite® 2015	1550 MPa	24	5.7%
Araldite® 2015-1	1590 MPa	21	4.2%

Flexural properties (ISO 178)

Cure 16 hours at 40°C

	Flexural modulus (MPa)	Flexural strength (MPa)
Araldite® 2015	1650	43
Araldite® 2015-1	1800	43

Lap Shear Strength after Thermal cycling

25 cycles (-30°C to 70°C to -30°C)

Cure 16 hours at 40°C

	Lap Shear Strength after Thermal cycling (MPa)
Araldite® 2015	19.3
Araldite® 2015-1	21.4


Glass transition temperature (DMA)

Cure 1 hour at 80°C


	Glass transition temperature by DMA (°C)
Araldite® 2015	78°C
Araldite® 2015-1	80°C



Chemical resistance : ageing tests - immersion in different media

Araldite® 2015
Cure 16 hours at 40 °C



Araldite® 2015-1
Cure 16 hours at 40 °C



Climatic testing : tropical weathering (40 °C/92% humidity)**Thermal resistance : heat ageing at 70 °C**

CONCLUSION & RECOMMENDATIONS

We can conclude that Araldite® 2015-1 is directly equivalent to Araldite® 2015, in terms of performance and mechanical properties. However we recommend to our customers to check that the product is suitable for their specific application.



Huntsman Advanced Materials
(Switzerland) GmbH
Klybeckstrasse 200
4057 Basel
Switzerland

Tel: +41 (0)61 299 11 11
Fax: +41 (0)61 299 11 12

www.aralditeadhesives.com

Huntsman Advanced Materials warrants only that its products meet the specifications agreed with the user. Specified data are analysed on a regular basis. Data which is described in this document as 'typical' or 'guideline' is not analysed on a regular basis and is given for information purposes only. Data values are not guaranteed or warranted unless if specifically mentioned.

The manufacture of materials is the subject of granted patents and patent applications; freedom to operate patented processes is not implied by this publication.

While all the information and recommendations in this publication are, to the best of Huntsman Advanced Material's knowledge, information and belief, accurate at the date of publication, **nothing herein is to be construed as a warranty, whether express or implied, including but without limitation, as to merchantability or fitness for a particular purpose. In all cases, it is the responsibility of the user to determine the applicability of such information and recommendations and the suitability of any product for its own particular purpose.**

The behaviour of the products referred to in this publication in manufacturing processes and their suitability in any given end-use environment are dependent upon various conditions such as chemical compatibility, temperature, and other variables, which are not known to Huntsman Advanced Materials. It is the responsibility of the user to evaluate the manufacturing circumstances and the final product under actual end-use requirements and to adequately advise and warn purchasers and users thereof.

Products may be toxic and require special precautions in handling. The user should obtain Safety Data Sheets from Huntsman Advanced Materials containing detailed information on toxicity, together with proper shipping, handling and storage procedures, and should comply with all applicable safety and environmental standards.

Hazards, toxicity and behaviour of the products may differ when used with other materials and are dependent on manufacturing circumstances or other processes. Such hazards, toxicity and behaviour should be determined by the user and made known to handlers, processors and end users.

Except where explicitly agreed otherwise, the sale of products referred to in this publication is subject to the general terms and conditions of sale of Huntsman Advanced Materials LLC or of its affiliated companies including without limitation, Huntsman Advanced Materials (Europe) BVBA, Huntsman Advanced Materials Americas Inc., Huntsman Advanced Materials (UAE) FZE, Huntsman Advanced Materials (Guangdong) Company Limited, and Huntsman Advanced Materials (Hong Kong) Ltd.

Huntsman Advanced Materials is an international business unit of Huntsman Corporation. Huntsman Advanced Materials trades through Huntsman affiliated companies in different countries including but not limited to Huntsman Advanced Materials LLC in the USA and Huntsman Advanced Materials (Europe) BVBA in Europe.

All trademarks mentioned are either property of or licensed to Huntsman Corporation or an affiliate thereof in one or more, but not all, countries.