

Safety Steps and Procedures To Follow Prior To Applying Cor-Ban® 35 Undyed:

- 1.) Always refer to the safety data sheet (SDS) prior to applying **Cor-Ban® 35 Undyed** if you have any questions regarding regulatory information about this product.
- 2.) Always wear gloves, a protective suit, an apron, boots, and eyewear to prevent **Cor-Ban® 35 Undyed** from making contact with the skin and eyes.
- 3.) Make sure there is proper airflow in the area where **Cor-Ban® 35 Undyed** will be applied.
- 4.) Make sure there are no sparks, open flames, hot surfaces, or other heat and fire ignition sources in the area where **Cor-Ban® 35 Undyed** will be applied.
- 5.) Keep **Cor-Ban® 35 Undyed** away from any combustible materials or sources.
- 6.) Wear a respirator to prevent inhalation of fumes from **Cor-Ban® 35 Undyed** especially if the ventilation in the area where **Cor-Ban® 35 Undyed** will be applied is insufficient.
- 7.) Cure sealants to recommendations set by the manufacturer prior to applying **Cor-Ban® 35 Undyed**.
- 8.) Vacuum and wipe surfaces so that moisture and other foreign material that is on them can be removed.
- 9.) Clean surfaces with the following aliphatic naphtha based wipe solvents, such as **Sur-Prep® 3160**, **Sur-Prep® 3167**, and **D-5640NS/ZC-640**.



Areas To Mask Prior To Applying Cor-Ban® 35 Undyed:

- 1.) Mask areas that will not to be coated, such as:
 - * Electrical Connectors
 - * Pins In Sliding Surface Contact
 - * Joints In Sliding Surface Contact
 - * Control Cables
 - * Pulley and Quadrant Cable Grooves
 - * Bushing and Bearings For All Types, which includes lined Teflon
 - * Silicone or Rubber Seals
 - * High Temperature Areas
 - * Wire Bundles
 - * Lubricated Surfaces
 - * Drain Valves
 - * Oxygen System Components (i.e. Bottles, Pressure Metering and Indicating Equipment and Connections)



Part of

& ADDEV
MATERIALS

Methods For Applying Cor-Ban® 35 Undyed:


1.) Use the following equipment for applying **Cor-Ban® 35 Undyed**.

- * HVLP Guns
- * Airless Spray Equipment
- * Aerosol
- * **Formit®** Extension Wands-For use with all **Zip-Chem®** aerosols to reach difficult to access areas, such as stringer edges.

HLVP Gun



- * **Formit®** 360° Spray (White Tube) Wand
- * **Formit®** Fan Spray Spray (Blue Tube) Wand
- * **Formit®** 180° Spray (Black Tube) Wands



Formit® 360° Spray
Demonstration Video



Formit® Fan Spray
Demonstration Video



Formit® 180° Spray
Demonstration Video



Temperature For Applying Cor-Ban® 35 Undyed:

1.) The temperature that **Cor-Ban® 35 Undyed** needs to be applied at should fall between 40°F and 100°F (4°C and 38°C).


Cor-Ban® 35 Undyed Product Information

- 1.) **Cor-Ban® 35 Undyed** is a high solids, low volatile, high penetration, water displacing, and long lasting non-decorative coating with a transparent yellow tint and offers a fast dry time and thin film with long lasting corrosion inhibiting properties.
- 2.) **Cor-Ban® 35 Undyed** is free of chromates, heavy metals, and has low toxicity and VOC levels.
- 3.) **Cor-Ban® 35 Undyed** dries quickly, is solvent removable, has a high solids percentage of >51%, and has a film that is non-tacky, thixotropic, and non-sagging.
- 4.) **Cor-Ban® 35 Undyed** has a very low dry film weight of < 1 mil (25 microns) required to surpass specification.
- 5.) **Cor-Ban® 35 Undyed** provides 2000 hours of salt spray protection, does not crack or flake to -40°F (-40°C),

Areas Where Cor-Ban® 35 Undyed Should Be Applied:

1.) **Cor-Ban® 35 Undyed** should be applied on:

- * Any Faying Surface
- * Stingers
- * Formers
- * Upper Edge Floor Beams
- * Wheel Wells
- * Pressure Deck
- * Center Wing Sections
- * Interior Fuselage
- * Landing Gear Wells



Tips For Applying Cor-Ban® 35 Undyed:

Focus the application process of **Cor-Ban® 35 Undyed** on all faying surfaces to ensure joint penetration and then then coat the entire area before moving on to the next section.

Inspect the surface for proper coating under stringers, formers, and other structures that are not in the line of sight.




The applied **Cor-Ban® 35 Undyed** coating should be continuous and free of voids. Runs, drips, sags, etc, are allowed provided that the drain holes and cross drains for where **Cor-Ban® 35 Undyed** should drain out of are not blocked. If the drain holes or cross drains become blocked, then wipe up the excess **Cor-Ban® 35 Undyed** using clean, dry gauze, or rags.

The **Cor-Ban® 35 Undyed** material will exhibit slight sags or wavy material lines on inclined surfaces in some situations. Immediate attention with a paint brush, however, will eliminate thick runs and sags. Extremely thick areas or puddles need to be wiped up quickly using solvents that are listed below in the removal instructions.

Thickness For Cor-Ban® 35 Undyed Including Tips For Measuring That Thickness:

The application thickness of **Cor-Ban® 35 Undyed** should be approximately 1.0 to 1.5 mils (25-38 microns) wet and .75 mils (19 microns) dry. For measuring the wet film thickness of **Cor-Ban® 35 Undyed**, use protection for your hand so that you can push **Zip-Chem®** 's **Wet Film Thickness Gauge** as shown below into the **Cor-Ban® 35 Undyed** material via hand after the **Cor-Ban® 35 Undyed** has been allowed to flow for a few minutes.

The thickness of the **Cor-Ban® 35 Undyed** can be determined by the visible tracks in the wet film that are left by the gauge fingers of the **Wet Film Thickness Gauge**. The dry film thickness of **Cor-Ban® 35 Undyed** may be verified using paint thickness instruments.



Tips For Drying Cor-Ban® 35 Undyed:

Cor-Ban® 35 Undyed typically will dry to a hard, tack free film in 45 minutes to 2 hours. These dry times should be accurate provided that adequate ventilation was utilized and that the **Cor-Ban® 35 Undyed** material was applied within the thickness range that was called out in the paragraph for the thickness that the dry material of **Cor-Ban® 35 Undyed** should be applied at under Tips For Measuring The Thickness of **Cor-Ban® 35 Undyed** section. The speed at which **Cor-Ban® 35 Undyed** dries and cures at is also influenced by humidity and temperature.

Methods For Removing Cor-Ban® 35 Undyed:

1.) **Cor-Ban® 35 Undyed** can be removed with an aliphatic naphtha based wipe solvents or its equivalents. **Cor-Ban® 35 Undyed** can also be removed with corrosion preventive compound/corrosion inhibiting compound removers, such as **Sur-Prep® 3160**, **Sur-Prep® 3167**, **D-5640NS/ZC-640**, and **Zip-Strip™ 125M**.



2.) Cured **Cor-Ban® 35 Undyed** can be removed with **Sur-Prep® 3160**, **Sur-Prep® 3167**, and **Zip-Strip™ 125M**



Part of



Cor-Ban® 35 Undyed Instruction Manual

Cor-Ban® 35 Undyed Product Pictures, Zip-Chem® Product Packaging Part Numbers, and Other Materials To Purchase:

Cor-Ban® 35 Undyed

- *Case of 12 of 16 fl oz (473 mL) Aerosols-**006710**
- *Case of 12 each Quart (946 mL)-**101482**
- *8 oz (227 gram) Brush In Cap-**101477**
- *Case of 4 each Gallon (4 each of 3.8 Liter) Cans-**009410**
- *5 Gallon (18.9 Liter) **Pail-006708**
- *55 Gallon (208 Liter) Drum-**006709**
- *Specialized forms of packaging available upon request

Sur-Prep® 3160

- *Case of 12 of 16 fl oz (473 mL) Aerosols-**010938**
- *Case of 4 each Gallon (4 each of 3.8L) Cans-**008578**
- *5 Gallon (18.9 Liter) Pails-**008579**
- *55 Gallon (208 Liter) Drum-**008580**
- *Case of 6 Canisters of Towelettes-**100026**
- *Case of 100 Individual Towelettes-**011844**
- *Specialized forms of packaging upon request

Zip-Strip™ 125M

- *Case of 12 of 16 fl oz (473 mL) Aerosols-**102614**
- *Case of 4 each Gallon (4 each of 3.8L) Cans-**102608**
- *5 Gallon (18.9 Liter) Pails-**102609**
- *55 Gallon (208 Liter) Drum-**102610**
- *Specialized forms of packaging available upon request

Sur-Prep® 3167

- *Case of 12 of 16 fl oz (473 mL) Aerosols-**103765**
- *Case of 4 each Gallon (4 each of 3.8L) Cans-**103762**
- *5 Gallon (18.9 Liter) Pails-**103763**
- *55 Gallon (208 Liter) Drum-**103764**
- *Specialized forms of packaging available upon request

D-5640NS/ZC-640

- *Case of 12 of 16 fl oz (473 mL) Aerosols (**D-5640NS**)-**002070**
- *Case of 4 each Gallon (4 each of 3.8L) Cans (**ZC-640**)-**009430**
- *5 Gallon (18.9 Liter) Pails (**ZC-640**)-**002155**
- *55 Gallon (208 Liter) Drum (**ZC-640**)-**008181**
- *Special forms of packaging available upon request (**ZC-640**)

Wet Film Thickness Gauge

***100266**

250 Masking Tape Tan (Can Be Certified TO SAE-AMS3721) | Apron | Boots

Tin Foil | Gloves | Protective Suit | Protective Eyewear | HVLP Guns

Aliphatic Naphtha Based Wipe Solvents or Equivalents | Airless Spray Equipment | Paint Thickness Instruments | Respirator | Paint Brush

Formit® Wands (12 Assemblies Per Package)

- *Formit®-18-Fan-**006224**
- *Formit®-18-180-**006226**
- *Formit®-18-360-**006227**
- *Formit®-18-STD-FOG-**008352**
- *Formit®-18-90-FOG-**008353**
- *Formit®-29-360-**101321**
- *Formit®-36-360-**009131**
- *Formit®-48-360 with metal sleeve-**009132**
- *Formit®-48-360 without metal sleeve-**100424**
- *Formit®-48-Fan-**008460**
- *Formit® Sample Pack (3 each of Formit®-18-Fan, Formit®-18-180, Formit®-18-360, Formit®-18-STD-FOG-**100107**)

← 1 Gallon (3.8 Liter) Cans

← NSN: 8030-01-615-4751 Gallon (3.8 Liter) (QPL)

← *16 Fluid Ounce (473 mL) Aerosol

← 8030-01-516-6254 (16 fl oz (473 mL) Aerosol (QPL))

Additional Cor-Ban® 35 Undyed NSN's: 8030-01-531-7364 (5 Gallons (18.9 Liter) (QPL)), 8030-01-615-4749 (Undyed) (QPL), 8030-01-615-4738 (8 oz (227 gram) Brush In Cap QPL), 8030-01-531-7362 (Quart (946 mL) (QPL)),

Sur-Prep® 3160 NSN: 6850-01-633-9843 (16 fl oz (473 mL) Aerosol); **D-5640NS NSN:** 8030-01-597-6958 (16 fl oz (473 mL) Aerosol)

Zip-Strip™ 125M NSN's: 6850-01-695-8514 (5 Gallon (18.9 Liter) Pail), 6850-01-707-8887 (16 fl. oz (473 mL) Aerosol)

Formit® NSN's: 4730-01-612-9914, 4730-01-661-8773 (**Formit®-18-Fan**); 6850-01-492-2942 (**Formit®-18-360**); 4730-01-632-0156 (**Formit®-18-STD-FOG**); 6850-01-517-0963 (**Formit®-18-90-FOG**); 1560-01-658-8943 (with metal sleeve), 4730-01-659-5461 (without metal sleeve) (**Formit®-48-360**); 4730-01-632-0157 (**Formit®-48-Fan**)

For application questions regarding **Cor-Ban® 35 Undyed**, contact **Zip-Chem® Aviation Products** at (1) 408 782 2335 or zipchem@addevmaterials.com.



Part of

